

# **Polyether Polyol YD-330N**

Release Date: 2019.04.17 Version: 2.0

### **Application**

YD-330N is a glycerin initiated polyether polyol with high primary hydroxyl content. It is suitable to produce high-resilience foam, cold-curing PU foam and flexible integral skin foam.

### **Specification**

Appearance	Colorless liquid
Viscosity@25 ℃ (mPa.s)	800~1000
Colority (APHA)	≤50
Hydroxyl Value (mgKOH/g)	32~36
K <sup>+</sup> (ppm)	≤5
Water Content %	≤ 0.05
Acid Value (mgKOH/g)	≤ 0.1
pH Value	5~7

## **Package**

We can supply galvanized iron drum, plastic bag, IBC, tank container or car tank for packing and transportation.

### Storage

Protect from atmospheric moisture. Keep container tightly closed and dry. Avoid prolonged exposure to heat and air. The temperature recommended for storage is  $15\sim35^{\circ}$ C. For long term storage in tank, nitrogen protection is recommended.

#### **Shelflife**

12 months under proper storage.

#### Matters need attention

Please refer to the "material safety data sheet" or follow local laws and regulations.